



CODE COMPLIANCE INSPECTION CHECKLIST – DRYWALL PRODUCTS
IBC 2006 REFERENCES ASTM C645-04 & ASTM A1003-02a

Requirement	Code Reference	Specification Requirements	Verification Process	Detail Process	MRI Compliance
Protective Coating	IBC 2006 ASTM C645-04	Corrosion Protection Options G40 Minimum or a protective coating with equal corrosion resistance	Mill Certifications, Elcometer Test to measure coating thickness	MRI Steel Framing has mill certifications available for each coil used to produce our steel framing. MRI specifies on each purchase order our minimum requirements to ensure code compliance.	YES
Base Metal Thickness	IBC 2006 ASTM C645-04	Each gauge has a minimum thickness before the protective coating is applied. 25 gauge = .0179 22 gauge = .0269 20 gauge = .0299	Measure thickness with a micrometer.	Each coil's thickness is measured with a micrometer during the receiving process. A random sampling of finished product is measured with a micrometer.	YES
Marking and Identification	IBC 2006 ASTM C645-04	Each stud or track must be marked with Company Name Minimum Steel Thickness Minimum Yield Strength Minimum Coating Weight	Visually inspect for label, stencil, or embossing.	MRI Steel Framing utilizes a world-class marking, inkjet coding computerized high-resolution printhead to label each piece of stud and track produced.	YES
Yield Strength	IBC 2006 ASTM A1003-02a	Minimum yield strength is 33 ksi	The way to verify yield strength is to have the product tested. The test ultimately destroys the sample.	MRI Steel Framing has mill certifications available for each coil used to produce our steel framing. MRI specifies on each purchase order the minimum requirements to ensure code compliance.	YES

201 Mississippi Street
Gary, IN 46402
Phone: 630-616-1850 Fax: 219-886-3341